

WATER REPELLENT

TDS20 Rev7 17/02/20

Concrete and Masonry Weatherproofer

DESCRIPTION

Westox Water Repellent is a clear formulated poly functional silane siloxane, providing maximum protection for concrete and masonry surfaces while allowing the surface to breathe.

USES

Westox Water Repellent penetrates and chemically reacts with all cementitious surfaces, preventing spalling and re-bar corrosion by locking out water and harmful waterborne contaminants such as CO². Westox Water Repellent does not film form and will not discolour or otherwise alter the appearance of concrete and masonry surfaces.

FEATURES

- ✓ Maximum water repellency
- ✓ Alkali Stable
- ✓ UV stable
- ✓ Cost effective
- ✓ Protection barrier against chloride laden water
- ✓ Can be applied to dry or damp surfaces
- ✓ Chemically bonds to surface, providing long term durability
- ✓ Reduces efflorescence

TECHNICAL DATA

Colour	Clear
Active Ingredient Content	12-14 (W/W)%
Components	One
Application Method	Roller, brush or low pressure fan jet pump spray
Drying times	Touch 20-40 minutes @ 25°C
Full cure time	7 days
Theoretical coverage per coat (2 flood coats required)	Brick 2 - 5m ² per Litre Concrete 5m ² per Litre Concrete (steel trowel) 7.5m ² per Litre.

NOTE

Coverage rates are intended as a guideline only. The texture and absorption characteristics of the surface will determine the actual coverage rate.

LIMITATIONS

Do not apply if rain is imminent.

Westox Water Repellent will react with airborne water vapour. Do not leave lid off container. Not recommended for below grade waterproofing or application where water pressure is from within the wall.

Westox Water Repellent will not prevent penetration through unsound or cracked substrates.

If Water Repellent is applied on or near buildings containing foodstuff, to prevent contamination they should be removed prior to application until the material has fully dispersed.

To prevent damage to nearby shrubbery and landscaping, cover or protect with a drop sheet.

This product will permanently mark and stain glass, mirrors, auto paints and powdered coatings, therefore take required action to prevent product from contacting these surfaces by masking or covering prior to application.

If product does come in contact with these surfaces wipe off immediately with white spirits.

PREPARATION

Surface cleanliness is critical to final appearance of substrates treated with Westox Water Repellent.

All oil, grease, form release agents and air pollution deposits must be removed prior to application.

All surfaces are to be structurally sound.

Mortar joints and masonry that has voids, or is cracked, or contains weak or unsound material must be repaired prior to application.

New concrete, new masonry and restoration work must reach full 28 day cure strength before application. Should high salt content be present, desalinate with Westox Cocoon prior to application.

HORIZONTAL SURFACES

Wipe off any excess material sitting on top of low porosity tiles or tracking may occur.

APPLICATION

Westox Water Repellent is a single component solution, ready to use from the container.

The substrate surface temperature should be above 5°C and below 35°C.

To provide adequate coverage in a minimum amount of time, use low pressure airless (knapsack) spray and flood coat the surface, starting at highest point.

Apply in a uniform manner in sufficient quantity to completely wet out the substrate.

Overlap each pass to avoid gaps and areas of insufficient coverage.

Apply second coat, wet on wet i.e. while the first coat is still wet.

Should high salt levels be present desalination is recommended prior to the application of Westox Water Repellent refer to Westox Cocoon Data Sheet.

This product is not suitable for application by conventional high pressure spray equipment that will atomize or vapourise the product. Application should be carried out by low pressure (knapsack) garden type sprayer or suitable airless equipment that does not atomize or vapourise. Flood coating is the general term stated for application.

CLEAN UP

Wash all equipment immediately after use in white spirit.

PACKAGING

5 Litre.

20 Litre.

SHelf LIFE

6 months in un-opened container.

SAFETY

Refer to Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.

Provide adequate ventilation during application. Repeated or prolonged contact may cause injury to skin or eyes. Repeated or prolonged inhalation of vapour may cause respiratory irritation or intoxication. Do not cut or weld containers.



Westgate Pty Ltd
16 Frost Road Campbelltown NSW 2560
Ph: 61 2 4628 5010 Fax: 61 2 4628 5020
Email: info@westox.com Website: www.westox.com