

PLASTALITE TUCKPOINT

TDS19 Rev7 28/09/23

DESCRIPTION

Tuckpoint is a fine sand, lime and Pozzuolanic material with a small amount of cement designed to provide a mortar mix with a moderate strength which will not be detrimental to the brick or stone where it is used.

USES

A ready formulated product for traditional tuckpointing. The material can also be used for pointing sandstone where the appearance of masons putty is required. Do not use Mortar Modifier if using for pointing sandstone.

FEATURES

- ✓ Available in White, Off White, Buff & Black
- ✓ Gunable
- ✓ Easy to use
- ✓ Consistent quality
- ✓ Compatible with other mortars
- ✓ Sacrificial in a salt environment
- ✓ Minimum shrinkage after tooling
- ✓ Non staining of stone

TECHNICAL DATA

Setting time	30 to 45 minutes for initial set
S.G.	1.25
Compressive Strength	7 - 8 MPA

COVERAGE

Tuckpointing - 5mm x 2mm	20kg = approximately 1000L/m.
Repointing stone - 5mm x 20mm	20kg = approximately 130L/m.

APPLICATION

Apply with brick key for traditional tuckpointing. For stone joints rake out to a minimum of 20mm deep and apply with pointing gun or trowel to previously dampened stone. New pointing should be kept damp for a minimum of 4 days to ensure full cure.

MIXING

Add Tuckpoint Powder to Mortar Modifier and mix to a useable consistency. Mortar Modifier will ensure mortars cure to the correct strength without the need to moisture cure.

PACKAGING

20kg bag.

SHELF LIFE

6 months in unopened bag.

SAFETY

Refer to Westlegate Pty Ltd Safety Data Sheet (SDS) for instructions.



Westlegate Pty Ltd
16 Frost Road Campbelltown NSW 2560
Ph: 61 2 46285010 Ph: 1300 WESTOX
Email: info@westox.com Website: www.westox.com