

GROUTING MORTAR

TDS45 Rev4 17/02/20

DESCRIPTION

Westox Grouting Mortar is a two part mix used in conjunction with Westox Crack Stitching Bars.

USES

Westox Grouting Mortar is used as a bedding mortar for Westox Crack Stitching Bars when carrying out repairs to cracks in brickwork, stonework and other masonry structures.

FEATURES

- ✓ Easy mixing.
- ✓ High strength.
- ✓ Easy placement.
- ✓ Gunable or trowelable.
- ✓ Fast setting.

TECHNICAL

Setting time 3 hours set time, 30 days full cure.
Compressive Strength 65MPA after 30 day cure.

COVERAGE

Joint Size – 10mm wide, 35mm deep
Approximately 30 Lineal Metres per 21kg kit.

MIXING

Only mix required amount needed. Add powder (Part A) to a portion of the liquid (Part B) until the required workable consistency is reached.

APPLICATION

Thoroughly wet down raked out joints to remove dust and debris and to control suction. Allow joints to become visually dry before placement of mortar. Place approximately 10mm of grout to rear of joint and push in reinforcing bar. Fill joint to face and pack grout tight to fully encapsulate the bar.

CLEAN UP

Wash all equipment in fresh water immediately after use.

PACKAGING

21kg Kit - Part A Powder 15kg bag & Part B Liquid 5 Litres.

SHELF LIFE

6 months in unopened container.

SAFETY

Refer to Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.