

WX COLOURCOTE ANTI-FLASH

TDS08 Rev6 17/02/20

DESCRIPTION

A single pack, waterbased anti-corrosive coating that can be applied over galvanised metal surfaces, or aged Colourbond.

USES

A surface coating for new or existing galvanised metal sheeting to enhance the character and life of the metal.

FEATURES

- ✓ Excellent gloss retention
- ✓ Excellent adhesion
- ✓ Easily applied

- ✓ Economical to use
- ✓ Can be overcoated
- ✓ U.V. stable, excellent colour retention
- ✓ Wide colour range

TECHNICAL DATA

 $\begin{array}{lll} \mbox{Volume Solids} & 50\% + -1 \\ \mbox{Specific Gravity} & 1.13 \underline{+} 0.05 \\ \mbox{Flash Point} & \mbox{Not applicable} \end{array}$

Finish Gloss
Touch Dry @ 20°c 5 minutes
Full Dry 1 hour

PREPARATION

Do not apply coating if temperature is below 10°c or above 35°c.

Do not apply coating if rain is imminent.

Sound paint may be overcoated.

New surfaces

Apply a degreaser or solvent wipe all new galvanised surfaces to remove pressing oils etc. Wash off and allow to dry before commencing application.

Old surfaces

The surface should be treated, should be clean and sound, free from oil, grease, flaking paint, laitance and materials deleterious to the adhesion of the coating system.

To areas of excessive rust, apply one (1) coat of a proprietary brand zinc rich primer and allow to dry. Ensure that all fixings are properly secure.

APPLICATION

Application is by brush, roller or spray to prepared, pre-primed surfaces at the rate of 6 - 8m² per litre. Apply a second coat at the rate of 6 - 8m² per Litre, following a minimum 4 hour drying period between coats.

CLEAN UP

Wash all equipment in fresh water immediately after use.

PACKAGING

15 Litre.

SHELF LIFE

12 months.

SAFETY

Refer to Westlegate Pty Ltd Safety Data Sheet (SDS) for instructions.



Westlegate Pty Ltd
16 Frost Road Campbelltown NSW 2560
Ph: 61 2 4628 5010 or 1300 937 869

Email: info@westox.com Website: www.westox.com