

AP GLAZECOAT

TDS10 Rev7 13/07/23

DESCRIPTION

A high performance two pack U.V. stable acrylic urethane with outstanding durability, providing a finish with maximum gloss and colour retention.

USES

As an anti-graffiti coating and for areas of special finish. eg. hand rails, food preparation areas, car parks, petrol stations and any other surfaces which require a high resistance to solvents.

FEATURES

- ✓ Excellent colour retention
- ✓ Excellent abrasion resistance
- ✓ Can be recoated
- ✓ Suitable for interior and exterior surfaces
- ✓ Will not yellow

TECHNICAL DATA

Colour	Clear
Finish	Full gloss
Volume Solids	40%
Specific Gravity	0.99
Chemical resistance	Excellent
Flash Point	27°C (<i>when parts A & B mixed</i>)

PREPARATION

The surface to be treated should be clean and sound, free from oil, grease, flaking paint, laitance and materials deleterious to the adhesion of the coating system.

Not recommended for below grade waterproofing.

New concrete should be a minimum of 28 days old before application commences.

All holes and cracks are to be repaired prior to coating.

Do not apply if temperature is below 10°C or above 35°C.

Do not apply if rain is imminent.

Concrete

If surface is porous, prime first with AP Glazecoat let down 20% with Westox AP Glazecoat Thinners, applied at the rate of 8 - 10m² per Litre.

Allow a minimum of 4 hours before proceeding with topcoat.

Metal

Prior to application, ensure that the surface is intact, free from contaminants such as oil, grease, water etc. All damaged areas should be made good with primer, use a proprietary zinc rich epoxy as primer/undercoat.

Timber

Fill and sand all holes and defects. Remove dust. If clear finish required, thin first coat with Westox AP Glazecoat Thinners at 50% and apply as a sealer, followed by two coats of AP Glazecoat.

APPLICATION

Mixing

Mix all of base (Part A) with all of hardener (Part B), or in the ratio of four (4) Part A to one(1) Part B by volume for small requirements. Use a power mixer for a minimum of 1 minute. Allow to stand 10 - 20 minutes before using. Pot life up to 8 hours working time.

Brush or Roller

Use brush for small difficult areas. Roller is recommended for small to medium areas.

Spraying

Conventional (pressure 300-450kPa) or airless (pressure 14-17 MPA) equipment set up.

Thinning

Use Westox AP Glazecoat Thinners up to 25% volume for conventional spray and up to 15% volume for airless spray.

Application may be undertaken at the coverage rate of 8 - 10m² per Litre, per coat.

Two coats required.

A minimum of two hours drying time between coats.

Material will be touch dry in 30 minutes.

CLEAN UP

Wash all equipment with Westox AP Glazecoat Thinners immediately after use.

PACKAGING

5 Litre Kit - Part A 4 Litre, Part B 1 Litre

20 Litre Kit – Part A 16 Litres, Part B 4 Litres.

SHELF LIFE

12 months.

SAFETY

Refer to Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.

Material is flammable and special care should be taken for transportation.

Keep away from sparks or open flames.

Avoid continued skin contact with material.

The wearing of protective articles is recommended.

When used in confined spaces provide sufficient ventilation.



Westgate Pty Ltd
16 Frost Road Campbelltown NSW 2560
Ph: 61 2 46285010 Fax: 61 2 46285020
Email: info@westox.com Website: www.westox.com