

BRICK SLIP MORTAR

TDS118 Rev0 21/03/22

DESCRIPTION

Westox Brick Slip Mortar is a cement-based pointing mortar formulated to be used with a wide range of powered and manual grouting guns or hand placement.

USES

Designed for pointing mortar joints in Brick Slip and laminated brick veneer cladding systems.

FEATURES

- ✓ Fast effective placement
- ✓ Assured mix ratios
- ✓ Reduced labour cost
- ✓ Available in a wide range of traditional and custom colours
- ✓ Colour consistent
- ✓ Weatherproof yet sacrificial

PREPARATION

All surfaces must be free of dust, dirt, oil or other substances which may inhibit the adhesion of the mortar. Water blasted surfaces should be allowed to dry for a minimum of 24 hours before repointing. Mortar joints must be dampened before application to control suction.

MIXING

Each 20kg bag of Westox Brick Slip Mortar will require approximately 3-4 Litres of water to reach a gunnable consistency. For wider joints a stiffer mix containing less water may be required.

APPLICATION & COVERAGE

Can be applied with powered/manual grouting guns, grouting bags or hand placement. A 20kg bag (13Litres) covers approximately 4m² of brickwork joints 10mm x 25mm.

SPECIFICATION

Based on a traditional 6:1:1 mix.
Compressive strength - 8 to 9 MPA after 28 day cure.
S.G - 1.54kg/Litre.
Standards AS3700 and M3 Mortar.

RESTRICTIONS

Do not apply during inclement weather.
Do not apply in temperatures below 5°C or above 30°C.
Do not allow new pointing to dry out too quickly.

CLEAN UP Wash all equipment with fresh water immediately after use.

PACKAGING 20kg bag.

SHELF LIFE 6 Months when stored in unopened bags in dry, cool conditions.

SAFETY Refer to the Westlegate Pty Ltd Safety Data Sheet (SDS) for instructions.



Westlegate Pty Ltd
16 Frost Road Campbelltown NSW 2560
Ph: 61 2 46285010 Fax: 61 2 46285020
Email: info@westox.com Website: www.westox.com