

2C LIMEWASH

TDS52 Rev6 17/02/20

DESCRIPTION

Westox Limewash is based on slaked rock lime using a number of traditional formulations. Various modern additives may also be deployed to obtain the performance characteristics required on any particular project. The selection of a particular blend depends on the substrate to be coated after discussion with the client.

COLOUR

White.

PREPARATION

Ensure that surfaces are free of loose and flaking paint, grease or other contaminants.

APPLICATION

Dampen porous surfaces immediately before applying Westox Lime Wash.

For previously painted surfaces it is recommended that light sanding is undertaken. For additional adhesion the surface may be primed using Westox RAP Primer (5 - 8m² per Litre) immediately before applying the Westox Lime Wash.

The Westox Limewash is applied at the rate of 5m² per litre per coat with two (2) coats normally required. Allow each coat to dry for two days before applying subsequent coats.

CLEAN UP

Wash all equipment in fresh water immediately after use.

PACKAGING

20 Litre.

SHELF LIFE

12 Months.

SAFETY

Refer to Westlegate Pty Ltd Safety Data Sheet (SDS) for instructions.