

MORTAR MODIFIER

TDS72 Rev6 17/02/20

DESCRIPTION

Mortar Modifier is an acrylic additive formulated to be used with Plastalite High Build Repair Mortar, Stone Repair Mortar and Fairing Coat.

USES

To be used as the gauging liquid in place of water in the above materials and provide characteristics to the mortars where an increase in strength, reduction in moisture transmission or extra thick or very thin applications are required.

FEATURES

- ✓ Provides maximum strength to all cement-based mortars, even in thin build applications.
- ✓ Reduces Moisture and Co² penetration when used in concrete repair work.
- ✓ Maintains High Alkalinity in Acidic environments.
- ✓ Reduces capillary and prevents efflorescence.
- ✓ Formulated to provide the maximum strength to the Westox mortar products.

PREPARATION

All surfaces must be free of efflorescence, dust, dirt, oil, paint or other substances which may inhibit the adhesion of the mortar.

Salt analysis and desalination may be required to increase the longevity of the intended mortar and protection of the building material. Refer to Westox Technical Department for more information on the Westox Cocoon Desalination System.

Acid cleaned surfaces should be washed down with a neutralising agent prior to application.

Water blasted surfaces should be allowed to dry for a minimum of 24 hours before application.

Bagging walls should be lightly dampened before application.

Do not apply during inclement weather.

Do not apply in temperatures below 5°C exceeding 30°C.

MIXING

Add powder to liquid and mix thoroughly, mix only the amount of material required. The amount of powder of the chosen Plastalite mortar Part A should be added to the Mortar Modifier Part B until the required consistency is obtained for the intended application.

CLEAN UP

Wash all equipment with fresh water immediately after use.

PACKAGING

5 Litre.

SHELF LIFE

12 months.

SAFETY

Refer to Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.

