

PLASTALITE REPOINT

TDS53 Rev3 17/02/20

DESCRIPTION

Repoint is a cement-based repointing mortar formulated to be used with a wide range of powered and manual grouting guns or hand placement.

USES

For repointing mortar joints in sandstone, brick and concrete blockwork.

FEATURES

- ✓ Fast effective placement
- ✓ Assured mix ratios
- ✓ Reduced labour cost
- ✓ Available in a range of traditional colours
- ✓ Formulations for Heritage Buildings available
- ✓ Weatherproof yet sacrificial

PREPARATION

Rake joints to a minimum of 20mm deep from finished face.

All surfaces must be free of efflorescence, dust, dirt, oil, paint or other substances which may inhibit the adhesion of the mortar. Salt analysis and desalination may be required to increase the longevity of the mortar and protection of the building material. Refer to Westox Cocoon Data Sheet.

Acid cleaned surfaces should be washed down with Westox Neutralising Solution prior to application.

Water blasted surfaces should be allowed to dry for a minimum of 24 hours before repointing.

Mortar joint must be dampened before application.

MIXING

Each 20kg bag of Repoint will require approximately 4-5 Litres of water to reach a gunnable consistency.

For wider joints a stiffer mix containing less water may be required.

CURING

For a moisture cure, mist twice a day for 3-4 days.

Full cure in 7 days.

SPECIFICATION

Based on a traditional 6:1:1 mix.

Compressive strength - 8 to 9 MPA after 28-day cure.

S.G - 1.54kg/Litre.

Standards AS3700 and M3 Mortar.

APPLICATION

1 x 20kg bag covers approximately 4m² of brickwork joints 10mm x 25mm.

RESTRICTIONS

Do not apply during inclement weather.

Do not apply in temperatures below 5°C or above 30°C.

Do not allow new pointing to dry out too quickly.

CLEAN UP

Wash all equipment with fresh water immediately after use.

PACKAGING

20kg bag.

SHELF LIFE

6 Months.

SAFETY

Refer to the Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.

