

## **PUTTY LIME**

TDS66 Rev4 17/02/20

### **DESCRIPTION**

Calcium Hydroxide – Putty Lime (General purpose and plastering Lime).

### **USES**

Limes are the base of most traditional mortars and plaster mixes. Limes should be slaked for a minimum of 14 days prior to use when using in finishing materials. Slaked Limes are also used in our pre-mixed mortars.

### **TECHNICAL DATA**

Putty Lime                      SG 1-1 to 1-3                      60% by weight water, 40% by weight Lime

### **PREPARATION**

To remove excess water from any of the Slaked Limes, pour the lime into a ring made in a sand pit and leave overnight.

### **MIXING**

Lime mortars can be mixed by hand or by mechanical mixers.

### **APPLICATION**

For specific uses and formulations containing Lime products consult our technical department.

### **PRECAUTIONS**

All Limes are caustic. Care should be taken and the correct safety equipment should be worn when handling these materials.

### **PACKAGING**

20 Litre & 200 Litre.

### **STORAGE**

Storage life is indefinite provided the Lime is not allowed to dry out.

### **SHELF LIFE**

3 years.

### **SAFETY**

Refer to Westgate Pty Ltd Safety Data Sheet (SDS) for instructions.

